



DW-9100FD

Product Description

- Conductive Non-Woven Fabric Double-coated Adhesive Tape.
- Differential Type Adhesive And Reworking Ability.
- Excellent Electrical Resistance.

Product Structure

| | |
|--|---------------------------------|
| | Conductive Acrylic Adhesive (A) |
| | Conductive Non-Woven Fabric |
| | Conductive Acrylic Adhesive (B) |
| | Release Liner |

Technical Data

| Classification | | Unit | Value | Test Method |
|-----------------------|---------|--------|----------|-------------------------------|
| Thickness | Backing | μm | 35 | KS T 1028 |
| | Total | | 50 | |
| Peel Strength | A | g/25mm | 800±100 | |
| | B | | Min 1300 | |
| Electrical Resistance | | Ω | 0.1 ↓ | Hioki 3540 500g Pressure |
| Holding Power | | mm/hr | 0.1 | SUS 304 1kg |
| Heat Resistance | | °C | Good | 110 °C × 500g Heating oven |

Dimensions

| Roll Width (mm) | Roll Length (M) |
|-----------------|-----------------|
| | |

Shelf Life

Product retains its performance and properties for 12 months from date of manufacture when stored in original cartons at room temperature & 50%RH

Company

436-8 Songma-Ri,
Daegot-Myeon, Gimpo-Si
Kyungki-Do, KOREA
TEL(82)-31-982-1999
FAX(82)-31-982-1145

www.dwc1999.com

The information given and the recommendations made herein are based on our experience and are believed to be accurate. No guarantee as to, or responsibility for, their accuracy can be given or accepted and no statement made herein is to be treated as a representation or warranty. In every case we urge and recommend that purchasers before using any product make their own tests to determine, to their own satisfaction, its suitability for their particular purposes under their own operating conditions. Such as evaluation should be repeated if materials are changed in any way or bought from a different source. No agent or representative of our has any authority to vary, omit or otherwise alter these terms.