




DW-9500T

Product Description

- On Side-Coated Conductive Acrylic Adhesive Tape
- Conductive Non-Woven Fabric
- Conductive Acrylic Adhesive

Product Structure



Technical Data

Classification		Unit	Value	Test Method	
Thickness	Backing	μm	45	KS T 1028	
	Total		60		
Peel Strength		g/25mm	1000	KS T 1028	
Holding Power		Sec	More than 3600	40℃ 500g Heating oven	
Surface Resistance		Ω	0.3↓	250g Pressure	Hioki 3540
Volume Resistance			0.1↓	1Kg Pressure	

Dimensions

Roll Width (mm)	Roll Length (M)

Shelf Life

Product retains its performance and properties for 12 months from date of manufacture when stored in original cartons at room temperature & 50%RH

Company

436-8 Songma-Ri,
Daegot-Myeon, Gimpo-Si
Kyungki-Do, KOREA
TEL(82)-31-982-1999
FAX(82)-31-982-1145

www.dwc1999.com

The information given and the recommendations made herein are based on our experience and are believed to be accurate. No guarantee as to, or responsibility for, their accuracy can be given or accepted and no statement made herein is to be treated as a representation or warranty. In every case we urge and recommend that purchasers before using any product make their own tests to determine, to their own satisfaction, its suitability for their particular purposes under their own operating conditions. Such as evaluation should be repeated if materials are changed in any way or bought from a different source. No agent or representative of our has any authority to vary, omit or otherwise alter these terms.